

# AXEON

## HF5 – Series Membrane Elements

---

**AXEON HF5 – Series Membrane Elements** are manufactured using the industry's leading membrane film technology. These membranes offer reliability, high performance and deliver consistent results. They provide increased production, high rejection rates and ultra low energy consumption by operating at low applied pressures.



### Benefits

- All Industry Standard Sizes
- Ultra Low Energy with High Flow Rates
- Improved RO System Performance
- Superior Quality and Cost Savings
- Individually Inspected, Qualified and Vacuum Tested
- Private Labeling and Customization Available

Know Higher Standards™

---

**AXEON**  
WATER TECHNOLOGIES



# AXEON HF5 – Series Membrane Elements

**AXEON HF5 – Series Membrane Elements** are the only elements on the market that operate at a pressure of only 80 psi. **AXEON HF5 – Series Membrane Elements** are available in all standard 2.5 – inch and 4 – inch commercial sizes and feature a tape – wound exterior. **AXEON HF5 – Series Membrane Elements** are the best choice to counter the negative effects of cold water temperatures on reverse osmosis – production. All elements are shipped dry for an indefinite shelf life, easier handling, and a lighter shipping weight. **AXEON HF5 – Series Membrane Elements** are 100% vacuum integrity tested and may also be ordered as individually wet tested.

## Operating Limits


- Membrane Type: Polyamide Thin – Film Composite
- Maximum Operating Temperature (°F / °C): 113 / 45
- Maximum Operating Pressure (psi / bar): 400 / 27.58
- pH Range, Continuous Operation\*: 2 – 11
- pH Range, Short Term Cleaning (30 Min.): 1 – 13
- Maximum Feed Silt Density Index (SDI): 5
- Chlorine / Chloramine Tolerance (ppm): 0
- Maximum Feed Flow Rate (gpm): 2.5" = 6  
4.0" = 14

\* Maximum temperature for continuous operations above pH10 is 95°F / 35°C.

## Product Specifications

Part Number	Description	Applied Pressure (psi / bar)	Permeate Flow Rate (gpd / m3/d)	Nominal Salt Rejection (%)	Part Number	Description	Applied Pressure (psi / bar)	Permeate Flow Rate (gpd / m3/d)	Nominal Salt Rejection (%)
208125	HF5 – 2514	80 / 5.52	225 / 0.85	98.50	200392	HF5 – 4014	80 / 5.52	600 / 2.27	98.50
208083	HF5 – 2521	80 / 5.52	400 / 1.51	98.50	200393	HF5 – 4021	80 / 5.52	1000 / 3.79	98.50
208084	HF5 – 2540	80 / 5.52	850 / 3.22	98.50	200394	HF5 – 4040	80 / 5.52	2500 / 9.46	98.50

**Warranty Evaluation Test Conditions:** Permeate flow and salt rejection based on the following test conditions – 550 ppm, filtered and dechlorinated municipal tap water, 77°F / 25°C, 15% recovery and the specified operating pressure. Minimum salt rejection is 96%. Permeate flows for warranty evaluation may vary +/-20%. Maximum pressure drop at 13 psig / 0.9 bar.



## Dimensions inch / mm:

Description	A	B	C	D	Description	A	B	C	D
HF5 – 2514	14 / 355.60	1.1 / 27.94	0.75 / 19.05	2.40 / 60.96	HF5 – 4014	14 / 355.60	1.1 / 27.94	0.75 / 19.05	3.95 / 100.30
HF5 – 2521	21 / 533.40	1.1 / 27.94	0.75 / 19.05	2.40 / 60.96	HF5 – 4021	21 / 533.40	1.1 / 27.94	0.75 / 19.05	3.95 / 100.30
HF5 – 2540	40 / 1016.00	1.1 / 27.94	0.75 / 19.05	2.40 / 60.96	HF5 – 4040	40 / 1016.00	1.1 / 27.94	0.75 / 19.05	3.95 / 100.30

All 2514, 2521 and 2540 elements fit nominal 2.50" I.D. membrane housings and all 4014, 4021 and 4040 elements fit nominal 4.00" I.D. membrane housings.

Proper start – up of reverse osmosis water treatment systems is essential to prepare the membranes for operating service and to prevent membrane damage due to overfeeding or hydraulic shock. Before initiating system start – up procedures, membrane pretreatment, loading of the membrane elements, instrument calibration and other system checks should be completed.

Avoid any abrupt pressure or cross – flow variations on the spiral elements during start – up, shutdown, cleaning or other sequences to prevent possible membrane damage. During start – up, a gradual change from a standstill to operating state is recommended as follows:

- Feed pressure should be increased gradually over a 30 – 60 second time frame.
- Permeate obtained from first hour of operation should be discarded.
- Avoid static permeate – side backpressure at all times.
- Cross – flow velocity at set operating point should be achieved gradually over 15 – 20 seconds.
- Maximum pressure drop across an entire pressure vessel (housing) is 30 psi / 2.1 bar.

Under certain conditions, the presence of free chlorine, chloramines and other oxidizing agents will cause premature membrane failure. Since oxidation damage is not covered under warranty, the manufacturer recommends removing all oxidizing agents by pretreatment prior to membrane exposure. Please contact the manufacturer or your supplier for more information.

Do not use this initial permeate for drinking water or food preparation. Keep elements moist at all times after initial wetting. To prevent biological growth during prolonged system shutdowns, it is recommended that membrane elements be immersed in a preservative solution. Rinse out the preservative before use. For membrane warranty details, please contact the manufacturer or your supplier for more information.

If operating limits and guidelines given in this product specification sheet are not strictly followed, the warranty will be null and void. The customer is fully responsible for the effects of incompatible chemicals and lubricants on elements. Use of any such chemicals or lubricants will void the warranty. These membranes may be subject to drinking water application restrictions in some countries: please check the application status before use and sale. The use of this product in and of itself does not necessarily guarantee the removal of cysts and pathogens from water. Effective cyst and pathogen reduction is dependent on the complete system design and on the operation and maintenance of the system.

No freedom from infringement of any patent owned by the manufacturer or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time,